

Technical data sheet AK8

Application: The AK8 is mainly used as vapour barrier in building construction, used to shut off gases and vapours. Effective against toxins from polluted construction materials, e.g. PCP, formaldehyde, PCBs. The PE-coated side of the film is corrosion-resistant to corrosive attack by wet cement (alkalinity)..

Material: Pure aluminium foil thickness 0,080 mm,
 PE coated on one side (amount applied: approx. 50 g/m²)

Characteristics:

	longitudinal direction	cross direction
Tensile strength	70 - 90 N/mm ²	70 - 90 N/mm ²
Elongation	6,94 %	7,98 %
Puncture resistance	0,50 J	0,50 J
Deformation at 80° C	- 0,02 %	+ 0,01 %

Vapour diffusion resistance: sd-value > 1'500 m equivalent air space thickness

Additional achievement of following standards: DIN 4102 B2

All data are based on our knowledge and experience. It's intended as an advice without legally binding.

8 January 2025